

MURANO SILVER/GOLD/BRONZ



The product can be pigmented.

Description of product

Very fine Grassello Paste for prestigious satin-semi shiny finishing with Venetian Stucco effect and shot reflections.

Application Field

This is an extra fine product for prestigious interior decoration, due to it's particular reflections which can be admired in the satin/semi-shiny finishing.

Product characteristics

MURANO SILVER/GOLD/BRONZ is a prestigious decorating product, composed of micro-filtered grassello, carefully mixed with special shot silver, gold and bronz powders. The colour shades can be personalized by using the colour scheme of the Tintometric system Luxury&Lime. The mixture of selected micro-marbles produces a stucco paste, ready to use, that permits a vast range of application methods able to satisfy the most sophisticated decorating needs. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market. The natural raw materials, accurately selected, give the MURANO SILVER/GOLD/BRONZ a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives.

Non-flammable and low odour.

Technical data	
Name	Murano Silver/Gold/Bronz
Composition	Magnesian aged quality lime putty, with micro-marbles and granule
Aspect	Highly dense paste
Color	Silver, Gold, Bronz
Dilution	Ready to use (if needed a dilution in water 0-5%)
Quantity per layer	approx. 5 - 6 m ² /kg
PH	13
Vapour permeability	SD - 0,04m (DIN 52615)
Water absorption	w - 0,3kg / (m ² h0,5) (EN1062-3:2001)
VOC class	VOC 5g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,30 kg/l
Packaging	5 - 20 kg buckets
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces in the first 12 hours from application

MURANO SILVER/GOLD/BRONZ

Instructions for use

- Prepare the base with a specific Primer, Isolante Acrilico or levelling base like Micro Primer Veneziano of Bericalce
- Application with stainless steel trowel
- Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base.
- Application of 2 coatings. After spreading the grade of brightness will be refined with spatola and/or special clothes. It's not advisable to apply more than 2 coats within the first 12 hours, as to permit the product to dry correctly
- Temperature of application: 5° to 35°C
- All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air
This process could last many months

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

BeriCalce ITALIA

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

bericalce.com