



MARMORINO MATT MADREPERLA "600"

MARMORINO MATT MATHER-OF-PEARL "600"

Description of product

Marmorino Matt Madreperla "600" mixed with selected grinded Australian Mother-of-Pearl for a prestigious decorative finishing - medium thickness.

Application Field

Prestigious decorations, medium thickness, matt finishing for interiors and exteriors.

Product characteristics

MARMORINO MATT MADREPERLA "600" interior and exterior finishing which permits to obtain, with more layers, the traditional Venetian Marmorino matt effect. An important characteristic is the grinded Mother-of-Pearl that gives the final product a natural sparkling. The colour shades can be personalized by using the colour scheme of the Tintometric system Luxur&Lime. Its accurate mixture renders the product soft and easy to apply. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market.

The natural raw materials, accurately selected, gives MARMORINO MATT MATT MADREPERLA "600" a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives.

Non-flammable and low odour.

Technical data	
Name	Marmorino Matt Madreperla "600"
Composition	"Dolomitic" Lime Putty (Grassello) minimum 12 month aged, marble powders and additives for less than 4%
Aspect	Dense paste
Color	Natural White
Dilution	Ready to use (if needed a dilution in water 0-5%)
Quantity per layer	approx. 1,2 - 1,6 m ² /kg
PH	13
Vapour permeability	SD - 0,04m (DIN 52615)
Water absorption	w - 0,3kg / (m ² h ^{0,5}) (EN1062-3:2001)
VOC class	VOC 4g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,75 kg/l
Packaging	5 - 25 kg buckets
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces from rain in the first 24 - 48 hours after application

MARMORINO MATT MADREPERLA "600"

Instructions for use

- Prepare the base with a specific Primer, Isolante Acrilico or levelling base like Isolante Ancorante Primer Berico
 - Application with stainless steel trowel
 - Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base
 - Application of 2 or more coatings. After spreading, the grade of smoothness will be refined with spatola and/or special tools. We suggest to apply the second layer after 4 hours in order to guarantee a correct fixing to the surface of the first layer
 - It's important that the product be of the correct consistence and dilution according to the temperature and absorption of the surface. In exteriors the product is guaranteed only if apply on a base of Intonachino Classico
 - Temperature of application: 5° to 35°C
 - All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air
- This process could last many months

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

BeriCalce ITALIA

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

bericalce.com