

TECHNICAL DATA 20

INTONACHINO FLOOR



Suitable for external uses.



The product can be pigmented.

Description of product

Compost of selected powders, grinded marbles and hydraulic binders to mix with special floor resins as primer base.

Application Field

Primer base for floors (Marmorino Floor series).

Product characteristics

INTONACHINO FLOOR is a levelling primer base, very resistant. Especially studied as primer base with a very strong adherence and its granular mix can well capture the following applications of the Marmorino Floor cycle. The colour can be personalized by using the colour scheme of the Tintometric system Luxury&Lime. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market. The natural raw materials, accurately selected, give INTONACHINO FLOOR a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives. Non-flammable and low odour.

Technical data	
Name	Intonachino Floor
Composition	Lime and Hydraulic binders, grinded marble and additives for less than 2%
Aspect	Powder
Color	Natural White
Dilution	with resin "Hard Mix Floor" at 33%
Quantity per layer	approx. 0,7 - 1,0 m ² /kg
PH	13 in water solution
Vapour permeability	SD - 0,01m (DIN 52615)
Water absorption	w - 0,005kg / (m ² h _{0,5}) (EN1062-3:2001)
VOC class	VOC 0g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Packaging	15 kg buckets
Storage	Keep in dry place with temperture min. 5° - 30°C max.
Notice	Protect the surfaces from rain in the first 24 - 48 hours after application

INTONACHINO FLOOR

Instructions for use

- Prepare the base with a specific Primer, HARD GRIP GRANULAR or SMOOTH, or rather SOLID GRIP di BeriCalce.
 - Blend carefully the product only with the special resin HARD MIX FLOOR and eventual colour until you obtain a homogeneous paste without lumps
 - Application with stainless steel/plastic trowel
 - Application of 1 or more coats
 - Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base
 - Once the product is spreaded, level and trowel the surface with a plastic trowel
 - Temperature of application: 5° to 35°C
 - All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air
- This process could last many months

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

Date of revision 1 05.02.2021

Date of revision 2 10.10.2024

BeriCalce S.r.l.

Via Piave, 23

36033 Isola Vicentina (VI) - ITALIA

Tel./Fax (+39) 0444 929102

Tel. (+39) 0444 654919

Skype: bericalce

info@bericalce.com

bericalce.com