

TECHNICAL CHART 114

CTW 057

Description of product

Anti-yellowing acrylic catalyst for Seal Varnish Bico Matt 05 / Satin 30 that forms a uniform and waterproof film and protect the treated surfaces exposed to extremely high degrees of humidity.

Application field

It is used as a catalyst in two-component varnishes "Seal Varnish", for matt or satin finishings.

Product characteristics

CTW 057 catalyzes the two-component varnishes in order to protect the treated surfaces, forming a uniform waterproof film, matt or satin, which has the following characteristics:

- excellent adherence to the major part of surfaces, if dry and properly treated;
- great resistance to usury;
- great flexibility.

Technical data	
Name	CTW 057
Composition	Acrylic
Aspect	Milky liquid
Color	Transparent
Catalysis ratio	5:1 (every 5 liters of two-component varnish, 1 liter of hardener is needed)
Dilution	Ready to use
VOC class	VOC 72 %
Packaging	0,2 liters packs
Storage	The product remains unchanged if kept in a closed and sheltered environment at a temperature between 5 - 35 °C. Protect from frost!
Notice	<ul style="list-style-type: none"> • Add the catalyst under stirring and allow to rest for at least 5 minutes. • Avoid using preheaters. • Mix the product well before use. • Use the mixed product within 3 hours. • Do not dispose of paint residues in the sewers. • The equipment should be washed immediately after use with water.

CTW 057

Instructions for use

- Pour CTW 057 into Seal Varnish Bico Matt 05 / Satin 30 and mix thoroughly
- Application with spray or brush.
- The product is applied in 2 or more coats.
- Apply the next coat after the hardening of the previous one.
- Do not apply below 15 °C.

Note

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.09.2017

BeriCalce S.r.l.

Via Odorico da Pordenone, 18

36100 Vicenza - ITALIA

Tel./Fax (+39) 0444 929102

Tel. (+39) 0444 654919

Skype: bericalce

info@bericalce.com

bericalce.com