



Suitable for external uses.



The product can be pigmented.

TECHNICAL **CHART 130**

INTONACHINO POWDER 500

Description of product

Decorative powder finish based on lime, hydraulic binders, and selected grinded marble (500 microns) for prestigious finishes with a "Venetian Intonachino" effect, medium-fine thickness.

Application Field

Luxury decorations for interiors and exteriors.

Product characteristics

INTONACHINO POWDER 500 is an interior and exterior granular finishing which permits to obtain, with more layers, the traditional "Venetian Intonachino" finishing effect with chiaroscuro shades. T

Its fine-to-medium grain creates a delicate yet textured surface, suitable for balanced decorative finishes that blend elegance and a natural appeal.

The product, thanks to its naturalness, can be coloured with pastel light colours of the Tintometric system Luxury&Lime. The accurate composition makes the product very resistant after application. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market.

The natural raw materials, accurately selected, give INTONACHINO POWDER 500 a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives. Non-flammable and odorless.

Technical data

Name	Intonachino Powder 500
Composition	Lime and Hydraulic binders, grinded marble and additives for a percentage less than 4%
Aspect	Powder
Color	Natural White
Dilution	25% with water
Quantity per layer	approx. 1,25 kg/m ²
PH	13
Vapour permeability	SD ~ 0,04 m (DIN 52615)
Water absorption	w ~ 0,3 kg / (m ² h0,5) (EN 1062-3:2001)
VOC class	VOC 0 g/l - wall paint and subcategory "L" max. value UE 2010 30g/l
Packaging	20 kg buckets
Storage	Keep in dry place with temperture min.5° ÷ 30°C max.
Notice	Protect the surfaces from rain in the first 24 ÷ 48 hours after application

INTONACHINO POWDER 500

Instructions for use

- Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base.
- Prepare the base with a specific primer, like FIX ARENA of Bericalce.
- Stir uniformly the product in clean water.
- Application with stainless steel trowel.
- * Application of 1 or more coatings.
- Each layer of the product must always be refined with a new trowel/sponge, using clean water.
- It's advisable to wait at least 12 hours before further coats to avoid marked shadows.
- The product must be applied with an uniform and constant method, alternating new trowel-sponge.
- It's important that the product be of the correct consistence and dilution according to the temperature and absorption of the surface.
- Temperature of application: 5° to 30°C

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue **28.06.2025**

Date of revision 1 **08.10.2025**

BeriCalce S.r.l.

ViaPiave, 23

36033 Isola Vicentina (VI) - ITALIA

Tel1. (+39) 0444 929102

Tel2. (+39) 0444 654919

Skype: bericalce

info@bericalce.com

bericalce.com